

广西金茂钛业有限公司

GUANGXI JINMAO TITANIUM CO.,LTD.

ADD: CHEMICAL INDUSTRIAL ZONE, TENG COUNTY, GUANGXI, CHINA

Tel: +86-774-7301933 Fax: +86-774-7290558 E-mail:dengmin@live.cn Web site:www.jinmao-ti.com

Technical Data Sheet

锐钛型颜料级钛白粉 Anatase Grade Titanium Dioxide

推荐使用范围 Application scope recommended

涂料、油墨、造纸、塑料、橡胶、人造纤维等行业。

Coating,ink,paper making,plastics,rubber,artificial fiber etc.

产品质量指标 Quality performance

质量指标质量指标 Specifications			Grade JMA-110	Grade JMA-100 (B101)
基本要求 Basic Requirements	TiO ₂ 含量% TiO ₂ Content	≥	98	98
	105℃挥发物% Volatile (105℃)	≤	0.5	0.5
	水溶物% Water Soluble	≤	0.6	0.6
	筛余物 (45μm 筛孔) % Residue(45μm)	≤	0.1	0.1
	Fe ₂ O ₃ 含量% Fe ₂ O ₃ Content	≤	0.06	-
条件要求 Condition Requirements	颜色 (与标样比) Colour (Compared with standard sample)		协商 negotiation	协商 negotiation
	相对散放射力 (与标样比) Relative Scatter Power (Compared with the standard sample)			
	消色力 (与标样比) Tint-reducing Power (Compared with the standard sample)	≥	105	100
	水悬浮液 PH 值 PH of Water Suspension		6.5-8.5	6.5-8.5
	吸油量 g/100g Oil Absorption	≤	22	24
	遮盖力 cm ² /g Covering Power	≥	250	200
	水分散性% Water Dispersibility	≥	80	60
	干粉白度 Dry Power Whiteness	≥	97.5	96
*1、用于颜色、相对散放射力检测的标样为我公司选定的标样或与客户商定的标样。2、用于消色力检测的标样为我公司选定的标样。3、商定指标除客户特殊要求，一般不作为常规分析。 *1、 We choosed the standard sample or negotiate with client which testing in colour and relative scatter radiation. 2、 We choosed the standard sample which testing in tinting power. 3、 Except the special request of client,the negotiate sample don't make analysis.				

产品包装规格 Package

珠光膜袋、纸塑复合袋：25kgs/包、500kgs/包、1000kgs/包。

Plastic woven bag,paper and Plastic valve bag:25kgs/bag,500kgs/bag,1000kgs/bag.

产品其他说明 Remark

产品的详细技术资料,敬请向供方联系索取;产品的质量指标以供方提供的检测报告为准。

For detail specifications,please contact your suppliers.Products quality performance is subject to suppliers' test report.